

AgNi

# Silver Nickel

**SCOPE:** This information refers to silver nickel wires, profiles and contact tips manufactured by blending of silver and nickel powder, compacting, sintering, extruding and drawing or rolling to final dimension.

## Designation of standard compositions

The Ni content of the material is designated in weight percent. Standard gradations are 10, 15, 20, 30 and 40 %.

## Characteristics

- » reliable anti-welding properties for switching currents up to 100 A
- » low contact resistance (nearly constant throughout the life time)
- » low arc erosion for switching currents up to 100 A
- » good arc migration and arc extinguishing properties
- » good formability, can be welded directly

## Physical Properties

The physical properties depend mainly on the Ni content.

MATERIAL	DENSITY [g/cm <sup>3</sup> ]	ELECTRICAL CONDUCTIVITY [m/(Ω·mm <sup>2</sup> )]	HARDNESS SOFT [HV1]	TENSILE STRENGTH SOFT [MPa]	ELONGATION SOFT [%]
AgNi10	10.3	54	50	240	38
AgNi15	10.2	48	55	260	34
AgNi20	10.1	46	60	270	32
AgNi30	10.0	41	65	320	25
AgNi40	9.8	37	70	350	20

## Applications

- » switches for domestic applications, auxiliary switches
- » contactors of switching currents up to 100 A
- » miniature circuit breakers, circuit breakers (asymmetrical combination with AgC)
- » power line relays, automotive relays
- » main contacts for ACB


## Microstructure

The Ni particles are deformed along the direction of extrusion into fibres




**AgNi10**

longitudinal section (parallel to the direction of extrusion)



**AgNi10**

cross section



**AgNi20**

cross section



#### **GERMANY**

Umicore AG & Co. KG  
Technical Materials  
Contact & Power Technology Materials  
Rodenbacher Chaussee 4  
63457 Hanau  
Phone: +49 6181 59 4869  
Fax: +49 6181 59 7 4869  
cpm.sales@umicore.com

#### **CHINA**

Umicore Technical Materials Suzhou Co. Ltd.  
#508-2 Zhujiang Road, SND  
215011 – Suzhou  
Phone: +86 512 6667 0800  
Fax: +86 512 6667 3230  
sales.utms@ap.umicore.com

#### **BRAZIL**

Umicore Brasil Ltda.  
Materiais Técnicos  
Rua Barão do Rio Branco, 368  
Guarulhos-SP  
07042-010  
São Paulo  
Phone: +55 11 2421 1371  
Fax: +55 11 2421 1180  
info@tm-cpm.com.br

#### **USA**

##### **Attleboro**

Umicore Technical Materials  
North America Inc.  
527 Pleasant Street, Building 11  
Attleboro, MA 02703  
Phone: +1 508 838 2064  
Fax: +1 508 838 2062  
sales.utmna@am.umicore.com

##### **Glens Falls**

Umicore Technical Materials  
North America Inc.  
9 Pruyin's Island Drive  
Glens Falls, NY 12801  
Phone: +1 518 932 0559  
Fax: +1 518 792 3162  
sales.utmna@am.umicore.com

[www.technicalmaterials.umicore.com](http://www.technicalmaterials.umicore.com)

The information and statements contained herein are provided free of charge and are for general information purposes only. They are believed to be accurate at the time of publication, but Umicore makes no representations or warranty of any kind with respect thereto, express or implied, about the completeness, accuracy, reliability, suitability or availability. Use or application of such information or statements is at the user's discretion, without any liability on the part of Umicore. Nothing herein shall be constructed as a license or recommendation to use. Umicore reserves the right to alter any product or service at its own discretion. All sales are subject to Umicore's General Terms and Conditions of Sale and Delivery (<http://www.umicore.de/service/agbs/agbs.htm>).

© 2013 Umicore AG & Co. KG. Printed in the Federal Republic of Germany