

# Ag/ZnO Silver Zinc Oxide

## Manufacturing process and delivery forms

The material is manufactured by blending silver and zinc oxide powder, compacting, sintering, and extruding in the form of wire, profile and contact tips.

The latter are available with a brazable silver layer and, optionally, with an additional layer of brazing alloy.

## Quality features of silver zinc oxide from Umicore

The components of the material are very evenly distributed. The material gets its excellent erosion resistance from the extreme level of compaction produced during the extrusion process.

## Composition

Silver zinc oxide is available as Ag/ZnO 92/8 with 92 % silver by weight.

Tungsten oxide as an active component greatly improves the welding resistance in general purpose applications.

## Key features

- » high resistance to welding on make
- » low contact resistance (comparable with other silver metal oxides)
- » low erosion in small current-limiting circuit breakers and motor-protection circuit breakers
- » free of toxic and carcinogenic components

## Applications

- » earth-leakage circuit breaker
- » motor-protection circuit breaker
- » circuit breaker
- » general purpose relays
- » small contactors

## Standard Composition

Ag/ZnO	ADDITIVE
SP	None
SPW	Tungsten Oxide

## Microstructure

The zinc oxide particles are homogeneously distributed in the cross section. The directional forming during extrusion leads to a slight orientation of the zinc oxide particles in the longitudinal section.



**Ag/ZnO 92/8 SPW**  
cross section



**Ag/ZnO 92/8 SPW**  
longitudinal section



#### **GERMANY**

Umicore AG & Co. KG  
Technical Materials  
Contact & Power Technology Materials  
Rodenbacher Chaussee 4  
63457 Hanau  
Phone: +49 6181 59 4869  
Fax: +49 6181 59 7 4869  
cpm.sales@umicore.com

#### **CHINA**

Umicore Technical Materials Suzhou Co. Ltd.  
#508-2 Zhujiang Road, SND  
215011 – Suzhou  
Phone: +86 512 6667 0800  
Fax: +86 512 6667 3230  
sales.utms@ap.umicore.com

#### **BRAZIL**

Umicore Brasil Ltda.  
Materiais Técnicos  
Rua Barão do Rio Branco, 368  
Guarulhos-SP  
07042-010  
São Paulo  
Phone: +55 11 2421 1371  
Fax: +55 11 2421 1180  
info@tm-cpm.com.br

#### **USA**

##### **Attleboro**

Umicore Technical Materials  
North America Inc.  
527 Pleasant Street, Building 11  
Attleboro, MA 02703  
Phone: +1 508 838 2064  
Fax: +1 508 838 2062  
sales.utmna@am.umicore.com

##### **Glens Falls**

Umicore Technical Materials  
North America Inc.  
9 Pruyin's Island Drive  
Glens Falls, NY 12801  
Phone: +1 518 932 0559  
Fax: +1 518 792 3162  
sales.utmna@am.umicore.com

[www.technicalmaterials.umicore.com](http://www.technicalmaterials.umicore.com)

The information and statements contained herein are provided free of charge and are for general information purposes only. They are believed to be accurate at the time of publication, but Umicore makes no representations or warranty of any kind with respect thereto, express or implied, about the completeness, accuracy, reliability, suitability or availability. Use or application of such information or statements is at the user's discretion, without any liability on the part of Umicore. Nothing herein shall be constructed as a license or recommendation to use. Umicore reserves the right to alter any product or service at its own discretion. All sales are subject to Umicore's General Terms and Conditions of Sale and Delivery (<http://www.umicore.de/service/agbs/agbs.htm>).

© 2013 Umicore AG & Co. KG. Printed in the Federal Republic of Germany