

Ag

Fine Silver and Silver Alloys

SCOPE: Silver, fine-grained silver and silver-copper which has been produced by melting-metallurgical methods.

- » Ag (fine silver, silver content > 99.9 %)
- » AgNi0.15 (fine-grain silver, Fg-Ag)
- » AgCu3 ...10 (hard silver)

Key Features

Ag

- » Highest electrical and thermal conductivity
- » Oxidation-resistant, lower contact resistance
- » Low weld-on-make resistance
- » Tendency for material migration in direct current applications

AgNi0.15 (fine-grained silver) and AgCu (hard silver, similar to Ag)

- » Higher wear resistance than Ag
- » resistance to welding higher than Ag but lower than AgNi
- » AgCu has a higher contact resistance than AgNi0.15, (increases with Cu content)
- » Very good ductility and brazing/welding properties

Applications

Switching currents up to 10 A

- » Relays
- » Switches for household appliances
- » Light and main switches
- » Auxiliary power switches

Delivery form

- » Wire
- » Profile
- » Contact tip



GERMANY

Umicore AG & Co. KG
Technical Materials
Contact & Power Technology Materials
Rodenbacher Chaussee 4
63457 Hanau
Phone: +49 6181 59 4869
Fax: +49 6181 59 7 4869
cpm.sales@umicore.com

CHINA

Umicore Technical Materials Suzhou Co. Ltd.
#508-2 Zhujiang Road, SND
215011 – Suzhou
Phone: +86 512 6667 0800
Fax: +86 512 6667 3230
sales.utms@ap.umicore.com

BRAZIL

Umicore Brasil Ltda.
Materiais Técnicos
Rua Barão do Rio Branco, 368
Guarulhos-SP
07042-010
São Paulo
Phone: +55 11 2421 1371
Fax: +55 11 2421 1180
info@tm-cpm.com.br

USA

Attleboro

Umicore Technical Materials
North America Inc.
527 Pleasant Street, Building 11
Attleboro, MA 02703
Phone: +1 508 838 2064
Fax: +1 508 838 2062
sales.utmna@am.umicore.com

Glens Falls

Umicore Technical Materials
North America Inc.
9 Pruyin's Island Drive
Glens Falls, NY 12801
Phone: +1 518 932 0559
Fax: +1 518 792 3162
sales.utmna@am.umicore.com

www.technicalmaterials.umicore.com

The information and statements contained herein are provided free of charge and are for general information purposes only. They are believed to be accurate at the time of publication, but Umicore makes no representations or warranty of any kind with respect thereto, express or implied, about the completeness, accuracy, reliability, suitability or availability. Use or application of such information or statements is at the user's discretion, without any liability on the part of Umicore. Nothing herein shall be constructed as a license or recommendation to use. Umicore reserves the right to alter any product or service at its own discretion. All sales are subject to Umicore's General Terms and Conditions of Sale and Delivery (<http://www.umicore.de/service/agbs/agbs.htm>).

© 2013 Umicore AG & Co. KG. Printed in the Federal Republic of Germany