

Technical Data Sheet BrazeTec D 801.1

Standard

ISO 17672
(AWS 5.8)
(DIN EN 1044)

Cu 110
(BCu-1b)
(CU101)

Nominal composition [wt.-%]

Permitted impurities max. [wt.-%]
Max. impurities [wt.-%]

Cu min. 99.90
Cd 0.01; Pb 0.025
0,04 (except O and Ag)

Technical data

Melting range of brazing alloy	approx. 1085 °C
Recommended brazing temperature	approx. 1120 °C
Density of brazing alloy	approx. 8.96 g/cm ³
Density of brazing paste	approx. 3.6 g/cm ³ (20 °C)
Viscosity	700 - 750 dPa s (Haake Viscotester VT 02, Sp.2, 20 ±2 °C)
Cleaning agent	Water
Shelf life	6 months in the original closed container storage temperature +5 to +30 °C. Stir well before use

Packaging

Standard 1; 5; 20 kg

Applications

BrazeTec D 801.1 is a flux free dosable paste with a high content of copper alloy powder. This dosable paste can be applied by air pressure or screw dispenser techniques. The paste has a good adhesion to the work piece and a long drying time after application. The brazing alloy shows good flowing and wetting properties. For wide brazing gaps (>0,1mm), e.g. they occur when the parts have wide tolerances, this BrazeTec D 801.1 paste only has a limited suitability. The copper brazing alloy can be used for brazing unalloyed and low, middle and high alloyed steels. The brazing process has to be carried out in vacuum or protective atmosphere. It is possible to harden brazed steel work pieces.

Details in product brochures or other advertisements about our products, equipment, plant and processes are based on our research and our experience in the field of applied engineering and are merely recommendations. It is not possible to infer any warranted qualities or warranted use from these details, unless they were expressly agreed as a warranted quality. We reserve the right to make technical modifications in the course of our product development.

The user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. This shall also apply to the protection of third party property rights as well as to applications and processes. The properties of samples and specimens are binding only if these have been expressly agreed to define the quality of the goods. Information on the quality and durability and other particulars are warranted only if these are agreed and designated as such. The specifications agreed with the user/purchaser in writing are relevant for the quality of the goods and if specifications have not been agreed in writing, the information contained in our technical data sheets, specifications or drawings.

Any additional or diverging agreements on the quality must be in writing. Any suitability of the product for the presupposed or customary use which supplements or diverges from the agreed quality is out of the question. Our General Conditions of Sale and Delivery shall apply; the current version is available at <http://www.saxonia-tm.de/en/TechnicalMaterials/agbs/>.