

Technical Data Sheet BrazeTec 6488

Standard

BrazeTec Standard
(ISO 3677)

(B-Ag64CuInMnNi 730/780))

Nominal composition [wt.-%]

Permitted impuritiesmax. [wt.-%]
Max. impurities [wt.-%]

Ag 64; Cu 26; Mn 2; Ni 2; In 6
Al 0.001; Bi 0.030; Cd 0.010; P 0.008; Pb 0.025; Si 0.05
0.3

Technical data

Melting rangeacc. Measurement	approx. 730–780°C
Brazing temperature	approx. 770°C
Density	approx. 9.6 g/cm ³
Shear strength acc. DINEN 12797	approx. 150 - 300 MPa (cemented carbide/steel)
Operating temp. of brazed joint	approx. -200°C to +200°C (without loss in strength)

Standard delivery forms*

Wire:	1.0 - 1.5 - 2.0 mm Ø
Rods:	1.0 - 1.5 - 2.0 mm Ø, 500 mm length
Ribbon:	0.1/ 0.2/ 0.3/ 0.4 mm thickness and 70 mm width
Preforms:	rings, shaped parts, sections, stamped and shaped parts, shims, discs, perforated plates

*Other delivery forms upon request

Applications

BrazeTec 6488 is a low melting silver based brazing alloy with excellent flow characteristics. The brazing alloy is suitable for brazing of cemented carbides and materials which are difficult to wet, such as tungsten, molybdenum, tantalum and chromium. The reachable strength of the joint depends from the parent metals.

BrazeTec 6488 will be used especially if parts are going to get a vacuum coating as e.g. TiN and therefore Zn-containing brazing alloys are not suitable.

It can be used for brazing with flame, with induction heating and in a furnace under protective atmospheres.

Typical applications are found e.g. in the tool industry.

Details in product brochures or other advertisements about our products, equipment, plant and processes are based on our research and our experience in the field of applied engineering and are merely recommendations. It is not possible to infer any warranted qualities or warranted use from these details, unless they were expressly agreed as a warranted quality. We reserve the right to make technical modifications in the course of our product development.

The user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. This shall also apply to the protection of third party property rights as well as to applications and processes. The properties of samples and specimens are binding only if these have been expressly agreed to define the quality of the goods. Information on the quality and durability and other particulars are warranted only if these are agreed and designated as such. The specifications agreed with the user/purchaser in writing are relevant for the quality of the goods and if specifications have not been agreed in writing, the information contained in our technical data sheets, specifications or drawings.

Any additional or diverging agreements on the quality must be in writing. Any suitability of the product for the presupposed or customary use which supplements or diverges from the agreed quality is out of the question. Our General Conditions of Sale and Delivery shall apply; the current version is available at www.umicore-brasage.fr/.

Druckdatum: 16.08.2018

Seite 1 von 1