

Tel.: +33 (1) 85 73 78 96

Fax: +33 (1) 43 60 52 58

commercial.umsf@umicore.com

## TD-STM-BT-E-0024-01

## **Technical Data Sheet BrazeTec 7291**

**Standard** 

BrazeTec Standard

(ISO 3677)

(B-Ag72Zn 710/730)

Nominal composition [wt.-%]

Permitted impuritiesmax. [wt.-%]

Ag 72; Zn 28

Al 0.001; Bi 0.030; Cd <0.010; P 0.008; Pb 0.025; Si 0.05

0.15

**Technical data** 

Melting range acc. Measurement

approx. 710 - 730°C (DSC -measurement)

Brazing temperature

Max. impurities [wt.-%]

approx. 730°C approx 8.43 g/cm<sup>3</sup>

Density
Shear strength acc. DIN EN 12797

with S235: min 150 MPa

Operating temp. of brazed joint

approx. -200 °C to +200 °C (without loss in strength)

Standard delivery forms\*

Wire:

1.0 - 1.5 - 2.0 mm Ø

Rods:

1.0 - 1.5 - 2.0 mm Ø, 500 mm length

Ribbon:

0.1/0.2/0.3/0.4 mm thickness and 70 mm width

Preforms:

rings, shaped parts, sections

\*Other delivery forms upon request

## **Applications**

BrazeTec 7291 is a low melting Cu- Free silver based brazing alloy.

It can be used for brazing unalloyed, low and high alloyed steels, copper and copper-based alloys as well as for nickel and nickel-based alloys.

It can be used for brazing with flame, with induction heating and in a furnace under protective atmospheres.

Typical applications are found e.g. in the refrigeration and air conditioning industry, automotive and in the electric industry.

Details in product brochures or other advertisements about our products, equipment, plant and processes are based on our research and our experience in the field of applied engineering and are merely recommendations. It is not possible to infer any warranted qualities or warranted use from these details, unless they were expressly agreed as a warranted quality. We reserve the right to make technical modifications in the course of our product development.

The user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. This shall also apply to the protection of third party property rights as well as to applications and processes. The properties of samples and specimens are binding only if these have been expressly agreed to define the quality of the goods. Information on the quality and durability and other particulars are warranted only if these are agreed and designated as such. The specifications agreed with the user/purchaser in writing are relevant for the quality of the goods and if specifications have not been agreed in writing, the information contained in our technical data sheets, specifications or drawings.

Any additional or diverging agreements on the quality must be in writing. Any suitability of the product for the presupposed or customary use which supplements or diverges from the agreed quality is out of the question. Our General Conditions of Sale and Delivery shall apply; the current version is available at <a href="https://www.umicore-brasage.fr/">www.umicore-brasage.fr/</a>.

Druckdatum: 31.08.2021 Seite 1 von 1