

Technical Data Sheet BrazeTec CB4

Standard

BrazeTec Standard
(ISO 3677)

(B-Ag70.5CuTi 780/805)

Nominal composition [wt.-%]

Ag 70.5; Cu 26.5; Ti 3

Permitted impurities max. [wt.-%]

Al 0.001; Bi 0.030; Cd 0.010; P 0.008; Pb 0.025; Si 0.05

Max. impurities [wt.-%]

0.15

Technical data

Melting range

approx. 780 - 805°C

Working temperature

approx. 850 - 950 °C

Density

approx 9,9 g/cm³

The strength values of joints brazed with active brazing alloy BrazeTec CB4 depend on the base materials and the brazing process parameters. In general it can be said that the joints fail in the ceramic if optimized process parameters have been used

Standard delivery forms*

Wire:

1.0 - 1.5 - 2.0 mm Ø

Ribbon:

0.1/ 0.2 mm thickness and 50 mm width

Preforms:

rings, shaped parts, sections, stamped and shaped parts, shims, discs, perforated plates

*Other delivery forms upon request

Applications

Active brazing alloy BrazeTec CB4 can be used for high temperature brazing of ceramics, ceramic metal-joints, graphite and diamonds. A minimum brazing temperature of 850 °C is recommended to get a joint to the ceramic. Higher brazing temperatures improve the wetting behavior. The brazing processes have to be carried out in vacuum or with argon (4.8 or purity 99,998%) as protective atmosphere. If the brazing process is carried out in vacuum the brazing temperature should not be higher than 900 °C to avoid the evaporation of silver. Active brazing alloys do not flow on ceramics. That's why the active brazing alloys always have to be applied between the surfaces to be brazed.

Details in product brochures or other advertisements about our products, equipment, plant and processes are based on our research and our experience in the field of applied engineering and are merely recommendations. It is not possible to infer any warranted qualities or warranted use from these details, unless they were expressly agreed as a warranted quality. We reserve the right to make technical modifications in the course of our product development.

The user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. This shall also apply to the protection of third party property rights as well as to applications and processes. The properties of samples and specimens are binding only if these have been expressly agreed to define the quality of the goods. Information on the quality and durability and other particulars are warranted only if these are agreed and designated as such. The specifications agreed with the user/purchaser in writing are relevant for the quality of the goods and if specifications have not been agreed in writing, the information contained in our technical data sheets, specifications or drawings.

Any additional or diverging agreements on the quality must be in writing. Any suitability of the product for the presupposed or customary use which supplements or diverges from the agreed quality is out of the question. Our General Conditions of Sale and Delivery shall apply; the current version is available at <http://www.umicore-brasage.fr>.

Druckdatum: 16.08.2018

Seite 1 von 1