

## Technical Data Sheet BrazeTec CSF 600 TD

### Solvent based brazing paste

BrazeTec CSF 600 TD is especially developed for the copper-brass radiator brazing process (CuproBraze). It is especially designed for application on the fin tips with special equipment. The binder system is solvent based and ensures fast drying, good adhesion and a residue free burnout under protective atmosphere.

### Standard

BrazeTec Standard CPO 600 (OKC 600, Patent US 5 378 294)

### Nominal composition [wt.-%]

Permitted impurities max. [wt.-%]

Cu Rem.; Sn 15.6; P 5.3; Ni 4.2

Al 0.010; Bi 0.030; Cd 0.010; O 0.050; Pb 0.025;

Zn 0.050; Zn + Cd 0.050

### Technical data

Melting range of brazing alloy

approx. 590 - 610 °C

Working temperature

approx. 650 °C

Metal content

> 85 wt.-%

Density of brazing paste

approx. 4.1 g/cm<sup>3</sup> (20 °C)

Grain size of brazing alloy powder

< 90 µm

Viscosity

3,4 ± 0,4 Pa s (Cone-Plate; 150 µm; D= 50/s; 20 °C)

Drying temperature

about 100 - 120°C, at workpiece

Cleaning agent

BrazeTec Cleaning Agent TD

Shelf life

min. 6 months, but only in the original sealed container at storage temperatures between +5 to +30°C. stir well before use

### Packaging

Standard 10; 25 kg

### Applications

BrazeTec CSF 600 TD is applied with special application equipment (fin tip machines) on the fin tips. The coated fins can then be dried at temperatures between 100 °C and 120 °C at the fins with standard drying processes (hot air, infrared). After drying the cores can be assembled.

The brazing process has to be carried out in protective atmosphere using nitrogen at a brazing temperature of about 650 °C depending on brazing furnace, furnace cycle, size of parts etc. The brazing time above 600 °C should be as short as possible and not longer than 4 minutes in case of brazing radiators to avoid critical tin-alloying of the thin fin material.

Details in product brochures or other advertisements about our products, equipment, plant and processes are based on our research and our experience in the field of applied engineering and are merely recommendations. It is not possible to infer any warranted qualities or warranted use from these details, unless they were expressly agreed as a warranted quality. We reserve the right to make technical modifications in the course of our product development. The user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. This shall also apply to the protection of third party property rights as well as to applications and processes. The properties of samples and specimens are binding only if these have been expressly agreed to define the quality of the goods. Information on the quality and durability and other particulars are warranted only if these are agreed and designated as such. The specifications agreed with the user/purchaser in writing are relevant for the quality of the goods and if specifications have not been agreed in writing, the information contained in our technical data sheets, specifications or drawings.

Any additional or diverging agreements on the quality must be in writing. Any suitability of the product for the presupposed or customary use which supplements or diverges from the agreed quality is out of the question. Our General Conditions of Sale and Delivery shall apply; the current version is available at <http://www.umicore-brasage.fr>.

Druckdatum: 16.08.2018

Seite 1 von 1