

Technical Data Sheet BrazeTec BlueBraze 2410

Standard

BrazeTec Standard
(ISO 3677)

(B-Cu44AgZnMnSn(Si)-690/750)

Nominal composition [wt.-%]

Ag 24.0; Cu 43.7; Zn 20.0; Mn 10.0; In 2.0; Si 0.3

Permitted impurities max. [wt.-%]

Al 0.001; Bi 0.030; Cd 0.010; P 0.008; Pb 0.025

Max. impurities [wt.-%]

0.15

Technical data

Melting range acc. ISO 17672

not applicable

Melting range acc. Measurement

approx. 690 – 750°C (DSC –measurement)

Brazing temperature

min. 750°C

Density

approx 8.4 g/cm³

Tensile strength acc. DIN EN 12797

with S235: 330 MPa; with E295: 480 MPa

Elongation at rupture

approx. 17 %

Electrical Conductivity

approx 2.4 m/ Ωmm²

Standard delivery forms*

Wire:

1.5 - 2.0 mm Ø

Rods:

1.5 - 2.0 mm Ø, 500 mm length

Strip:

0.1/ 0.2/ 0.25 / 0.3/ 0.4 mm thickness and 1.5 to 70 mm width

Preforms:

rings, shaped parts, sections

*Other delivery forms upon request

Applications

BrazeTec BlueBraze 2410 is a low melting silver based brazing alloy with excellent flow characteristics. It can be used for brazing any steels, copper and copper based alloys as well as for nickel and nickel based alloys. It can be used for flame or induction brazing procedures.

Typical applications are found e.g. in the refrigeration and air conditioning industry.

Note for user: The flux residues are corrosive and have to be removed

Details in product brochures or other advertisements about our products, equipment, plant and processes are based on our research and our experience in the field of applied engineering and are merely recommendations. It is not possible to infer any warranted qualities or warranted use from these details, unless they were expressly agreed as a warranted quality. We reserve the right to make technical modifications in the course of our product development.

The user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. This shall also apply to the protection of third party property rights as well as to applications and processes. The properties of samples and specimens are binding only if these have been expressly agreed to define the quality of the goods. Information on the quality and durability and other particulars are warranted only if these are agreed and designated as such. The specifications agreed with the user/purchaser in writing are relevant for the quality of the goods and if specifications have not been agreed in writing, the information contained in our technical data sheets, specifications or drawings.

Any additional or diverging agreements on the quality must be in writing. Any suitability of the product for the presupposed or customary use which supplements or diverges from the agreed quality is out of the question. Our General Conditions of Sale and Delivery shall apply; the current version is available at www.umicore-brasage.fr/.