

## Technical Data Sheet BrazeTec Degufit 3000

### Standard

Alloy-No. acc. ISO 9453	402 (Alloy)
ISO 3677	Sn97Cu3 (Alloy)
ISO 9454:2016	Typ 3.1.1.4 (Flux)

### Nominal composition [wt.-%]

Permitted impuritiesmax. [wt.-%]	Sn remainder; Cu 3 Pb 0.10; Sb 0.10; Bi 0.10; Ag 0.10; Au 0.05; In 0.10; Al 0.001; As 0.03; Cd 0.002; Fe 0.02; Ni 0.01; Zn 0.001
----------------------------------	--

### Technical data

Colour	grey
Melting range	approx. 227 - 310 °C
Metal content	min. 60 wt.-%
Chloride content	max. 9%
Density of soldering alloy	approx. 7,3 g/cm <sup>3</sup>
Density of soldering paste	approx. 2,4 g/cm <sup>3</sup> (20 °C)
Viscosity	300 - 500 dPa s (Haake Viscotester 02, Sp.2, 20 ±2 °C)
Residues	corrosive, soluble in water
Cleaning agent	Water
Shelf life	min. 24 months, but only in the original sealed container at storage temperatures between +5 to +30°C Stir well before use

### Packaging

Standard	250 g jar with brush
----------	----------------------

### Applications

BrazeTec Degufit 3000 it is suitable for plumbing copper tubes with fittings for potable water lines. It can be worked with flame or with resistant soldering clamps, too. The brush makes it easier to apply the paste on the copper tube in a thin layer and prevents an unwished contact with the skin. Prior to applying the paste the soldering areas have to be cleaned e.g. with a BrazeTec cleaning pad (metal free).

Besides the plumbing of tubes the paste can be used for soldering steel, copper, copper alloys, nickel and nickel alloys.

### Further comments

The paste has to be applied to the cleaned end of the tube in a thin layer. After you have put the tube end into the fitting it will be heated with flame or resistant soldering clamps till you will see a fillet.

Then soldering alloy will be fed to the joint by a wire of BrazeTec 3.

After soldering the paste residues have to be removed. This can be done by wiping or washing on the outer surfaces with a wet cloth. Potable water lines have to be rinsed referring DIN 1988 in

Details in product brochures or other advertisements about our products, equipment, plant and processes are based on our research and our experience in the field of applied engineering and are merely recommendations. It is not possible to infer any warranted qualities or warranted use from these details, unless they were expressly agreed as a warranted quality. We reserve the right to make technical modifications in the course of our product development.

The user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. This shall also apply to the protection of third party property rights as well as to applications and processes. The properties of samples and specimens are binding only if these have been expressly agreed to define the quality of the goods. Information on the quality and durability and other particulars are warranted only if these are agreed and designated as such. The specifications agreed with the user/purchaser in writing are relevant for the quality of the goods and if specifications have not been agreed in writing, the information contained in our technical data sheets, specifications or drawings.

Any additional or diverging agreements on the quality must be in writing. Any suitability of the product for the presupposed or customary use which supplements or diverges from the agreed quality is out of the question. Our General Conditions of Sale and Delivery shall apply; the current version is available at [www.umicore-brasage.fr/produits/brasures-industrielles-2/](http://www.umicore-brasage.fr/produits/brasures-industrielles-2/).