

Technical Data Sheet BrazeTec D807.1

Standard

ISO 17672
(AWS 5.8)
(DIN EN 1044)

CuP 284
(BCuP-5)
(CP 102)

Nominal composition [wt.-%]

Permitted impurities

Cu Rem.; Ag 15; P 5
max. [wt.-%] Al 0.01; Bi 0.030; Cd 0.01; Pb 0.025; Zn 0.05
Zn + Cd 0.05;
0.25

Max. impurities [wt.-%]

Technical data

Melting range acc. ISO 17672	approx. 645 - 800°C
Melting range acc. Measurement	approx. 645 - 800°C (DSC –measurement)
Recommended brazing temperature	approx. 720 °C
Density of brazing alloy	approx. 8.3 g/cm ³
Density of brazing paste	approx. 3.4 g/cm ³ (20 °C)
Metal content	approx. 85 wt.-%
Grain size of brazing alloy powder	< 63 µm
Viscosity	20 - 25 Pa s (Cone-Plate; 150 µm; D= 50/s; 20 °C)
Shear strength acc. DIN EN 12797	100 MPa (with Cu)
Operating temperature of joint	max. 150 °C (without loss of strength)
Cleaning agent	BrazeTec Cleaning Agent P
Shelf life	min. 6 months, but only in the original sealed container at storage temperatures between +5 to +30°C. stir well before use

Packaging*

Standard 1; 3; 5; 10 kg

Applications

BrazeTec D 807.1 paste contains a phosphorous-containing brazing alloy with good flow characteristics. The brazing alloy is suitable for joining copper to copper or copper-based materials. Due to its phosphorous content, you do not have to use an additional flux for brazing only copper to copper.

This brazing alloy is not allowed to be used if sulfur containing Medias may have contact with the joint during operating. Further it is not allowed to use this alloy for joining steels (Fe) or materials containing iron, nickel and cobalt as brittle phases will be formed in the joint. In refrigeration and air conditioning industries BrazeTec D 807.1 can be used for service temperatures down to -50°C. It can be used for brazing with flame, with induction heating and in a furnace under protective atmospheres. Typical applications are found e.g. in the electric industry and for the refrigeration and air conditioning industry.

Details in product brochures or other advertisements about our products, equipment, plant and processes are based on our research and our experience in the field of applied engineering and are merely recommendations. It is not possible to infer any warranted qualities or warranted use from these details, unless they were expressly agreed as a warranted quality. We reserve the right to make technical modifications in the course of our product development. The user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. This shall also apply to the protection of third party property rights as well as to applications and processes. The properties of samples and specimens are binding only if these have been expressly agreed to define the quality of the goods. Information on the quality and durability and other particulars are warranted only if these are agreed and designated as such. The specifications agreed with the user/purchaser in writing are relevant for the quality of the goods and if specifications have not been agreed in writing, the information contained in our technical data sheets, specifications or drawings.

Any additional or diverging agreements on the quality must be in writing. Any suitability of the product for the presupposed or customary use which supplements or diverges from the agreed quality is out of the question. Our General Conditions of Sale and Delivery shall apply; the current version is available at <http://www.umicore-brasage.fr>.