

Technical Data Sheet BrazeTec H 80 Paste

StandardDIN EN 1045
AWS A5.31-92RFH10
FB3-A**Based on**

boron compounds, fluorides

Technical Data

Working temperature range approx. 550 - 850°C
Colour white
Density approx. 1.6 g/cm³ (20°C)
Viscosity 80 - 160 dPa s (Haake Viscotester 02, Sp.2, 20 ±2°C)
Flux residues corrosive, water-soluble
Shelf life min. 6 months, but only in the original sealed container at storage temperatures between +5 to +30°C.
Avoid rapid changes in temperature.

Packaging

Standard 0.1; 1.0; 1.5; 3.0; 10; 40 kg

Applications

Flux for brazing cemented carbides and alloyed steels but also mild steel, copper and copper alloys as well as nickel and nickel alloys.

BrazeTec H 80 paste is suitable for all flame brazing and for induction brazing procedures.

Typical applications are found e.g. in the tool industry (cemented carbides, diamond segments), automotive and electric industry (contacts).

Flux BrazeTec h 80 is especially suitable for short brazing times (< 30 sec.)

Further Information

Stir well before use. Only homogeneously mixed paste will display constant and repeatable performance. Additions of water may negatively alter these parameters.

Flux residues are corrosive and have to be removed by washing or by pickling.

Details in product brochures or other advertisements about our products, equipment, plant and processes are based on our research and our experience in the field of applied engineering and are merely recommendations. It is not possible to infer any warranted qualities or warranted use from these details, unless they were expressly agreed as a warranted quality. We reserve the right to make technical modifications in the course of our product development.

The user must verify the suitability of our products and processes for the use or application intended by him on his own responsibility. This shall also apply to the protection of third party property rights as well as to applications and processes. The properties of samples and specimens are binding only if these have been expressly agreed to define the quality of the goods. Information on the quality and durability and other particulars are warranted only if these are agreed and designated as such. The specifications agreed with the user/purchaser in writing are relevant for the quality of the goods and if specifications have not been agreed in writing, the information contained in our technical data sheets, specifications or drawings.

Any additional or diverging agreements on the quality must be in writing. Any suitability of the product for the presupposed or customary use which supplements or diverges from the agreed quality is out of the question. Our General Conditions of Sale and Delivery shall apply; the current version is available at <http://www.umicore-brasage.fr>.